



DECOLATHER™ RECYCLED LEATHER VENEER BY FORMICA® GROUP

PRODUCT DESCRIPTION

dECOLATHER™ by Formica Group is recycled leather veneer made from pulverized leather fibers extracted from car seats and leather tanneries. dECOLATHER thickness is comparable to veneer and laminate at 0.8 mm or 1/32".

COLORS AND FINISH

dECOLATHER is available in 4ft. by 8 ft. sheets in 12 standard and 6 made to order colors, 3 finishes, and 1 thickness (0.8mm). Actual size of sheet is slightly larger, approximately 49.5inch by 97.5inch. Custom colors are available with a 30 sheet minimum order and longer lead times.

RECOMMENDED APPLICATION

dECOLATHER can be used on light-duty horizontal or vertical applications, including but not limited to casework of restaurants, bars, retail kiosks, coffee shops, and hotel reception desk surfaces.

PACKAGING

dECOLATHER can be packaged in a box or a pallet. Small quantities (5 or less) can be packaged in a double walled box rated at a minimum of 50lbs burst strength. Recommended box dimensions are 8"W x 8"H x 50"L.. The sheets should be rolled with the face of the sheet on the inside. The maximum number of sheets per box is 5. Larger quantities of dECOLATHER sheets (50+) should be packed on a pallet or crate. Use a maximum of 300 sheets of dECOLATHER per pallet or crate to avoid damage to the texture.

HANDELING

dECOLATHER sheets must be handled with care. Two people are needed when handling the sheets. Sheets must be handled by sliding when possible. When lifting the sheets, each person should hold opposite corners, tensing the sheets straight, creating a "U" shape.

FABRICATION AND ASSEMBLY

dECOLATHER sheets rely on adhesive for installation. If dECOLATHER sheets are rolled in a shipping carton they should be removed and laid flat. dECOLATHER and the substrates should be acclimated in the same environment for 72 hours in a room between 55°F and 90°F prior to installation with stable humidity levels. Both the dECOLATHER and substrate must be smooth, clean, dry and free of grease, dirt, dust, oil or any other foreign matter. The best way to apply dECOLATHER to a substrate is in a cold press at 35 to 50psi using PVA white glue. Vacuum forming capability would need to be determined by each fabricator shop. If press equipment is not available, high quality water based contact cement such as Formica® brand F-160 is recommended. Use 100% coverage on both the back of the dECOLATHER and face of substrate. Allow adequate time for contact cement to "tac-up". Tac-up takes about 40 minutes for water based contacts. Trapped gases can lead to bubbling or delamination of surface if not allowed to tac-up completely. A J-roller can be used to apply adequate pressure to bond dECOLATHER to substrate. dECOLATHER can be wrapped to tight ¼ inch radius. A 2 inch under wrap is necessary to prevent abuse of edge exposure. In most cases it is best to encapsulate the edges with metal, wood, plastic framing, or edge banding.

PANEL BALANCING

As with any wood based substrate surfacing product there will need to be a balancing sheet on the back for certain applications where a panel is not bound (i.e. doors, signage, cabinets etc.). The best balance is achieved using the same product on both sides using the same adhesive and bonded at same time. For less critical applications Formica recommends a backer in grade 91 or C2.

LIMITATIONS

dECOLATHER is designed for light duty horizontal and vertical applications for interior use only. Do not adhere directly to plaster or concrete. Do not use in areas exposed to temperatures exceeding 275°F, or areas of high humidity. dECOLATHER can puncture or tear so avoid sharp object impact or scuff. Exposed edges can "fluff" when abraded, thus edges need to be encapsulated in metal, wood, plastic framing, or edge banding.

MACHINING

dECOLATHER can be cut with a straight edge and razor knife. Routing edges can result in burrs and fuzzing so panels should be cut oversized and trimmed at the saw using triple chip blade configurations. CNC preferred settings are a speed of 200 in/min using a 4 flute 450 downward cutter. Recommended saw blades are an ATB alternate bevel cross cut with a scoring blade.

SUBSTRATE

Formica dECOLATHER should be bonded to MDF, particleboard or good hardwood plywood substrates. Gypsum board with an applied primer as used to hang wall paper is also appropriate. All materials should be acclimated for 72 hours in the same environment. Substrates should be sanded smooth and cleaned of all debris.

PERFORMANCE CHARACTERISTICS

ANSI / NEMA STANDARDS PUBLICATION – LD3 -2005

PHYSICAL PROPERTIES	LD3 TEST	
Surface Finish Gloss	3.2	5.0
Light Resistance	3.3	No Effect
Cleanability	3.4	21

STAIN RESISTANCE

Regeants 1-10	3.4	No Effect
Regeants 11-15		No Effect
Boiling Water Resistance	3.5	No Effect
Radiant Heat Resistance -sec	3.10	66 sec
Dimensional Change	3.12	
Machine Direction - 10		0.04
Cross Direction - 15		0.41

ASTM E84 FLAME 165 SMOKE 200 CLASS C

(BONDED TO FRPB USING PVA ADHESIVE)

ASTM D5053 CROCKING 4.5 OR SLIGHT TO NEGLIGIBLE

ASTM D4157 DOUBLE RUB NO WEAR AT 100,000 CYCLES



DECOLEATHER™ RECYCLED LEATHER VENEER BY FORMICA® GROUP

HOW TO SPECIFY

Surface (and appropriate backing sheet) shall be Formica Brand Laminate by Formica Group, Cincinnati, Ohio.

COLOR NUMBER

COLOR NAME

FINISH

TECHNICAL SERVICES

Full copies of a specific test report can be obtained by calling 1-800-FORMICA™ (option 2). All reports from independent research organizations and test labs apply only to the actual specimen or specimens studied and not to any similar materials or product nor to any production run of such material or products. Any information or suggestion concerning applications, specifications or compliance with codes or standards is provided solely for your convenient reference and without any representation as to accuracy or suitability. Formica Corporation disclaims any legal responsibility. The user must verify and test the suitability of any information or products for their own particular purpose or specific application.

LIMITED WARRANTY

Formica Corporation expressly warrants that, for a period of (1) one year from the date of first sale, Formica® Brand dECOLeather products will be reasonably free of defects in materials and workmanship, and that when properly handled and fabricated, will conform to applicable manufacturing specifications. Colors are subject to sheet to sheet variations. This limited warranty only applies to Formica® Brand dECOLeather which is stored, handled, fabricated and installed in the manner recommended by Formica Corporation. The warranty does not cover damage caused by improper installation, improper lamination, excessive humidity or use of a non-recommended adhesive. Mistreatment of any kind, including mechanical impact, scuffing caused by hard objects, water damage, plumbing leaks, fire damage, inadequate maintenance, or improper usage will void this Limited Warranty. Mistreatment of improper usage includes damage from moving heavy objects across the surface without adequate protection, rotating vacuum cleaners or brushes, and dropping heavy or sharp objects onto the recycled leather. Further excluded are problems due to extreme temperatures, heat or cold, sunlight, stains, rips, tears, gouges or indentations.

DISCLAIMER OF WARRANTIES

THE WARRANTIES SET FORTH HEREIN OR IN FORMICA CORPORATION'S WARRANTY DOCUMENTS WITH RESPECT TO A PRODUCT ARE THE ONLY WARRANTIES MADE BY FORMICA CORPORATION IN CONNECTION WITH THESE PRODUCTS, AND ARE EXPRESSLY IN LIEU OF ANY OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING WITHOUT LIMITATION, ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. PRODUCTS SOLD BY FORMICA CORPORATION ARE SOLD ONLY TO THE SPECIFICATION SPECIFICALLY SET FORTH BY FORMICA CORPORATION IN WRITING.

FORMICA CORPORATION'S SOLE OBLIGATION FOR A REMEDY TO BUYER SHALL BE REPAIR OR REPLACEMENT TO NON-CONFORMING PRODUCTS, OR AT THE OPTION OF FORMICA CORPORATION, RETURN OF THE PRODUCT AND REFUND OF THE PURCHASE PRICE. BUYER ASSUMES ALL RISK WHATSOEVER AS TO THE RESULT OF THE USE OF THE PRODUCTS PURCHASED, WHETHER USED SINGLY OR IN COMBINATION WITH OTHER SUBSTANCES.

LIMITATION OF LIABILITY

No claim by buyer of any kind, including claims for indemnification, whether as to quality or amount of products delivered or for no delivery of products, shall be greater in amount than the purchase price of the products in respect of which damages are claimed.

IN NO EVENT SHALL FORMICA CORPORATION BE LIABLE TO BUYER FOR ANY SPECIAL, INDIRECT, INCIDENTAL, RELIANCE, EXEMPLARY, OR CONSEQUENTIAL DAMAGES OR COVER, OR LOSS OF PROFIT, REVENUE OR USE, IN CONNECTION WITH, ARISING OUT OF, OR AS A RESULT OF, THE SALE, DELIVERY, SERVICING, USE OR LOSS OF USE OF THE PRODUCTS SOLD HEREUNDER, OR FOR ANY LIABILITY OF BUYER TO ANY THIRD PARTY WITH RESPECT THERETO. BUYER SHALL INSPECT FOR NONCONFORMITY PROMPTLY UPON RECEIPT.

Failure by buyer to give Formica Corporation written notice of claim within 30 days from date of delivery or, in the case of non-delivery from the date fixed for delivery, shall constitute a waiver by buyer of all claims in respect of such products.



Formica Corporation
10155 Reading Road
Cincinnati, Ohio 45241-5279
(800)367-6422